



**PLASTICS & NON-METALLICS
FOR INDUSTRY SINCE 1921**

FRANKLIN FIBRE – LAMITEX CORPORATION
P.O.Box 1768, Wilmington, DE 19899

Phone: (302) 652-3621
Fax: (302) 571-9754
e-mail: info@franklinfibre.com

Lamitex® XXX Tube Technical Data

Lamitex® XXX paper /phenolic convolute wrapped tubes are suitable for electrical and mechanical applications in high humidity conditions. XXX is a tropical grade laminate with the lowest moisture absorption rate of all paper phenolic formulations that also retains good electrical properties in high frequency applications.

<u>Mechanical Properties</u>	<u>Test Method:</u>			<u>Conditioning</u>	
	<u>EN 61212-2</u>	<u>Standard</u>	<u>Test Specimen</u>	<u>IEC 212</u>	<u>Values</u>
Flexural Strength	4.1	ISO 178	id>100 mm	1	110 MPa
Compressive Strength, Axial	4.2	ISO 604		1	130 MPa
Cohesion between layers	4.3	EN 61212-2	id<100 mm	1	145 MPa
 <u>Electrical Properties</u>					
Electric Strength in oil @ 90°C:					
Perpendicular to Laminations	5.1	IEC 243-1	3 mm wall thk	2	6.7 kV/mm
Parallel to Laminations	5.1	IEC 243-1	>3 mm wall thk	2	25 kV/ 25 mm
Insulation resistance after immersion in water		IEC 167	id>8mm and or od>10mm		200 M ohm
Permittivity 50 Hz & 1 MHz	5.2			4	
Dissipation Factor 50 Hz and 1 MHz	5.3	IEC 250		3	5.0
	5.3	IEC 250		3	0.03
 <u>Physical and Thermal Properties</u>					
Thermal endurance index @ 20,000 hrs	6.0	IEC 216		-	120°C T.I.
Density	7.2	IEC 1183-A	All	1	1.25 g/cm ³
Water Absorption	7.1	IEC 62-1		4	2 mg/cm ²

Conditioning: 1: 24h @ 23°C & 50%RH
2: 24h @ 23°C & 50%RH + 1hr in oil at 90°C
3: 96h @ 105°C + 1hr @ 23°C & 20%RH
4: 24h @ 50°C + 24hr in water at 23°C
5: 96h @ 105°C + 1hr in oil at 90°C

The standard mm length(s) for inside diameters 3 - 8.4 mm is 1500, 8.5 -10 mm is 1350, IDs >10 to 100 mm is 1350, 1500, or 1650 and >100 - 1250 mm is 1220, 1350, or 1650 mm.

All values are average test results from typical production material and extensive testing.
No Warranty is implied or guaranteed and testing is recommended for each application.

Epoxies • Phenolics • Melamine • Silicone • Sheets • Molded Shapes • Tubes • Cut to Size • Fabricated Parts • Vulcanized Fibre

FRANKLIN FIBRE – LAMITEX CORPORATION

August 20, 2009 Rev. b